





HYBRID SELF LEVELING SEALANT

Hybrid self-leveling sealant is a one-component self-leveling, silane modified polymer (SMP) based sealant ideal for horizontal applications. Its elasticity allows it to absorb continual movements of the **structure** caused by thermal changes without problems of cracking.

FEATURES & BENEFITS

TECHNICAL

- 1-component, no mixing required
- Self-leveling consistency, easily fills the cracks on the floor
- Waterproof; immediately seals water
- Possesses permanent elasticity
- High adhesion strength
- Capable of ±20% joint movement
- Paintable

APPLICATION AREAS

- Used for sealing of horizontal joints
- Waterproofing applications
- Interior and exterior areas
- Expansion joints between many different construction materials
- **Control joints**
- **Industrial floors**
- Driveways/Garages
- Sidewalks
- Decks

INSTRUCTIONS

- Before application, be sure that joint surfaces are clean, dry and free of all contamination.
- Apply sealant evenly, If necessary, use masking tape and remove the tape while the sealant is still wet.
- Joint dimension should allow for 6 mm minimum and 12 mm maximum thickness for sealant.
- Proper design is 2:1 width to depth ratio.
- If necessary, use back up material to adjust joint depth.

Absorbs Continual Movements of the Structure





Yesilbayır Mah. Simsir Sk. No: 22 Hadımköv - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88

www.akfix.com - info@akfix.com

Consumption (approx.)

Joint width	12 mm	20 mm	24 mm
Joint Depth	6 mm	10 mm	12 mm
Joint length / 600 ml	8 meters	3 meters	2 meters

Surface Preparation

Brush and remove dust before applying on concrete and other alkaline surfaces.

STANDARDS

Meets or exceeds the requirements of the following specifications:

CE marked for EN 15651 for façade applications.

RESTRICTIONS;

- Avoid application below +5 °C and above +35 °C.
- Do not apply on curing silicones.
- Minimum depth for working joint is 6 mm.
- Maximum expansion and contraction should not exceed 25% of average joint width.

STORAGE AND SHELF LIFE;

12 months if stored in its original package, away from direct sunlight and moisture, between +10 °C and +25 °C

SAFETY & DISPOSAL

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.





Yesilbayır Mah. Simsir Sk. No: 22 Hadımköv - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88

www.akfix.com - info@akfix.com

PROPERTIES

Chemical Base	: Hybrid Polymer		
Curing Mechanism	: Moisture Curing		
Density	: 1.39 ± 0.03 g/ml		
Consistency	: Self-Leveling		
Skin Formation Time	: 25±5 min. (23°C and 50% R.H.)		
Tack Free Time	: 90±10 min. (23°C and 50% R.H.)		
Curing Rate	: Min. 2.50 mm/day (23°C and 50% R.H.)		
Shore A Hardness	: 25±5	ISO 868 (After 28 days)	
Elongation at Break	:>300%	ASTM D412	
Tensile Strength	: 0.75-1.5 N/mm ²	ASTM D412	
Application Temperature	: +5°C to +35°C		

PRODUCT

Product Type	Volume	Package
Concrete Grey (Cartridge)	310 ml	12
Concrete Grey (Sausage)	600 ml	12
Concrete Grey (Aluminum pouch)	825 ml	12

DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.